

CHARACTERISTICS OF DEVELOPED FLEXIBLE POLYURETHANE FOAMS  
REINFORCED WITH COCONUT COIR FIBRES AND  
RECYCLED TYRES

CHAN WEN SHAN

A thesis submitted in  
fulfillment of the requirement for the award of the  
Degree of Master of Mechanical Engineering

Faculty of Mechanical and Manufacturing Engineering  
Universiti Tun Hussein Onn Malaysia

OCTOBER 2012

*“Special dedicated to my beloved parent and my sibling who always gave me support  
and encouragement”*



## ACKNOWLEDGEMENT

The section of acknowledgement is specially dedicated to those who made this research possible.

First, I am heartily thank to my supervisor, Prof. Hj. Mohd. Imran bin Ghazali, who gives encouragement, guidance, and support from the initial to the final stage of the research. Without his leading and knowledge contributed, especially in the field of noise and vibration, the research will not be finished as fast as one and half year. A special thank to him for looking the funds to support this research, especially obtained the Grant Research Assistance (GRA) to me. It gave a great financial support during the research period.

Thank you to my co-supervisor, Dr. Maizlinda Izwana bte Idris, who spends a lot of time on helping and guide me in the field of composite material. Her knowledge and advice save me when I faced problem in material preparation, foams developed as well as in mechanical testing.

In addition, I would like to thank to Mr. Fazlannuddin Hanur bin Harith and Mr. Shahrul Mahadi bin Samsudin who help me during the specimen fabrication stage and also during the mechanical and thermal testing. Thank to Mr. Md Zainorin bin Kasron who helps me to set-up the free vibration and vibration transmissibility test. Thank to Mr. Nizam bin Jamat who always willing to support me in specimen cutting. Thank to Mr. Anuar bin Ismail who assists me to conduct the SEM observation. Thank to Mr. An Amur Rahman bin Yunos who gives full cooperation when I went to metrology lab for size measurement.

The most important, thank to my beloved parent and sibling for their concern and support. A special thank to Kee Chung for his encouragement, understanding, supports, and helps when I faced difficulty in the research.

Last but not least, I would like express my regard and blessing to all of those who support me in any aspect during the completion of the research.

## ABSTRACT

Flexible Polyurethane (PU) foam is generally used in seat cushions of automotive seating for comfort and supporting the occupants. However, due to the demand for more comfortable compartment; seat cushions are now designed for better riding comfort and acoustic absorption which linked to the damping of foam. Incorporated treated coir fibres (F) and tyre particles (P) into polymeric material had improved the damping and strength of the material. In this research, flexible PU foams were reinforced with two fillers for the purpose of higher damping property and improve the mechanical strength. Five samples with 2.5wt% of filler loading were developed. The damping of samples was measured on sound absorption and vibration transmissibility test that generated at 1mm, 1.5mm, 0.1g, and 0.15g base excitation while their mechanical properties were examined through compression, tear resistance, and compression set. The morphology of samples was also observed by SEM in this research. The results showed that the foam composites produced have smaller cell size, in which the smallest was 840 $\mu$ m compared to 1290 $\mu$ m obtained in pure PU foam. The mechanical properties revealed that the strength of flexible PU foam increased with added treated coir fibres and recycled tyres. The best properties were shown in PU+2.5wt%(50F50P) which increased by 10.78% on the compressive modulus, 9.33% on the compressive strength, 14.49% on the static energy absorption, and 3.76% on the tear strength compared to pure PU foam. The sound absorption and vibration damping of the developed foams showed that more energy were absorbed and dissipated by these foams after fillers added. The PU+2.5wt%(80P20F) and PU+2.5wt%F presented an excellent sound absorption characteristics at 20mm and 40mm thickness, respectively, whereas PU+2.5wt%P, PU+2.5wt%(80P20F), and PU+2.5wt%(80F20P) showed higher vibration damping from the transmissibility test.



## ABSTRAK

Pada amnya, *Flexible Polyurethane (PU)* berbusa diguna dalam kusyen tempat duduk kenderaan untuk memberi keselesaan dan menanggung penggunaanya. Namun, atas permintaan pengguna supaya bahagian dalaman menjadi lebih selesa, kusyen tempat duduk kenderaan kini di rekabentuk untuk keselesaan dan penyerapan akustik yang lebih baik, dimana ianya berhubung kait dengan penyerapan pada bahan yang berbusa. Campuran sabut kelapa dirawat (F) dan serbuk tayar (P) ke dalam bahan polimer meningkatkan penyerapan dan kekuatan bahan. Dalam kajian ini, *flexible PU* berbusa diperkukuh dengan dua pengisian bagi tujuan meningkatkan penyerapan dan kekuatan mekanikal bahan. Lima sampel kajian dengan 2.5wt% pengisian telah dihasilkan. Penyerapan bahan komposit diukur dengan ujian penyerapan bunyi dan ujian kebolehpindahan getaran yang dilakukan pada 1mm, 1.5mm, 0.1g, dan 0.15g yang diuja pada tapak, manakala sifat-sifat mekanikal pula diperolehi melalui ujian seperti mampatan, rintangan koyak, dan set mampatan. Morfologi komposit pula diperolehi dari *SEM* dalam kajian ini. Keputusan ujian menunjukkan bahawa komposit berbusa yang dihasilkan mempunyai sel bersaiz lebih kecil, di mana yang paling kecil adalah 840µm berbanding dengan 1290µm yang diperolehi dari *PU* berbusa yang tulen. Sifat-sifat mekanikal menunjukkan bahawa kekuatan *flexible PU* berbusa meningkat dengan campuran sabut kelapa dirawat dan serbuk tayar kitar semula. Sifat-sifat yang terbaik ditunjukkan pada PU+2.5wt%(50F50P) dan ianya meningkat sebanyak 10.78% pada modulus mampatan, 9.33% pada kekuatan mampatan, 14.49% pada penyerapan tenaga statik, dan 3.76% pada kekuatan koyak berbanding dengan *PU* berbusa yang tulen. Penyerapan bunyi dan serapan getaran bahan yang di hasilkan menunjukkan bahawa ianya meningkat apabila bahan berbusa dicampur dengan pengisian, iaitu PU+2.5wt%(80P20F) dan PU+2.5wt%F dimana ianya boleh menyerap bunyi dengan baik pada ketebalan 20mm dan 40mm, manakala PU+2.5wt%P, PU+2.5wt%(80P20F), dan PU+2.5wt%(80F20P) pula boleh menyerap getaran dengan baik dalam ujian kebolehpindahan.

## CONTENTS

<b>TITLE</b>	<b>i</b>
<b>DECLARATION</b>	<b>ii</b>
<b>DEDICATION</b>	<b>iii</b>
<b>ACKNOWLEDGEMENT</b>	<b>iv</b>
<b>ABSTRACT</b>	<b>v</b>
<b>ABSTRAK</b>	<b>vi</b>
<b>CONTENTS</b>	<b>vii</b>
<b>LIST OF TABLES</b>	<b>xiii</b>
<b>LIST OF FIGURES</b>	<b>xv</b>
<b>LIST OF SYMBOLS</b>	<b>xxii</b>
<b>LIST OF ABBREVIATIONS</b>	<b>xxiv</b>
<b>LIST OF APPENDICES</b>	<b>xxvii</b>
<b>CHAPTER 1 INTRODUCTION</b>	<b>1</b>
1.1 Background of study	1
1.2 Problem Statement	4
1.3 Hypothesis of research	4
1.4 Objective of research	5
1.5 Scope of research	5
1.6 Significant of research	6
1.7 Expected outcome	6

1.8	Thesis organization	7
<b>CHAPTER 2</b>	<b>LITERATURE REVIEW</b>	<b>9</b>
2.1	Flexible polyurethane foam	9
2.1.1	Foam formula and generation	11
2.1.2	Foam development and its morphology	13
2.1.3	Foam production	15
2.2	Composite material	17
2.2.1	Flexible PU foam composite	19
2.2.2	Fillers	27
2.2.2.1	Natural fibre: coconut coir fibre and its properties	27
2.2.2.2	Post-consumer or recycling tyre	29
2.2.2.3	Reviews of coconut coir fibres and waste rubber added to composite material	31
2.3	Automotive seating foam	37
2.3.1	Comfort performance of seating foam	38
2.4	Nonlinear and viscoelastic characteristic	43
2.5	Properties of flexible PU foam: compression in static and dynamic	43
2.6	Energy absorption of cushioning	

	material	47
	2.6.1 Energy absorption mechanism in foam	48
2.7	Foam modeling	48
2.8	Vibration transmissibility	52
2.9	Foam-block system	54
	2.9.1 Dynamic behavior of flexible PU foam inserted to foam- block system	56
<b>CHAPTER 3</b>	<b>METHODOLOGY</b>	<b>60</b>
3.1	Methodology chart	60
3.2	Foam composites development	61
	3.2.1 Mould fabrication	62
	3.2.2 Filler preparation	63
	3.2.3 Foam composite designed and fabrication	64
	3.2.3.1 Foam production route	65
3.3	Vibration transmissibility test	68
	3.3.1 Experimental procedure	69
	3.3.1.1 Data acquisition technique	70
3.4	Fixture (frictional) losses determination	71
	3.4.1 Data acquisition technique	73
3.5	Constitutive of foam model	73
3.6	Acoustic absorption test	76
3.7	Physical and mechanical tests	77

3.7.1	Chemical analysis	77
3.7.2	Morphology study	78
3.7.3	Themogravimetric analysis	79
3.7.4	Density and compression tests	80
3.7.5	Tear resistance	82
3.7.6	Compression set	84

## **CHAPTER 4 FILLER CHARACTERISTICS AND FOAM PRODUCTION**

**86**

4.1	Filler characteristics	86
4.1.1	Microstructure of filler	86
4.1.2	Chemical composition	88
4.1.3	Thermal profile	90
4.2	Foam Production	94
4.2.1	Effect of fillers to foam production	96
4.3	Foam morphology	98
4.3.1	Distribution and bonding of fillers with matrix	101

## **CHAPTER 5 PHYSICAL AND MECHANICAL PROPERTIES**

**103**

5.1	Density	103
5.2	Compression force deflection	105
5.2.1	Compressive modulus and Strength	107
5.2.2	Energy absorption	110
5.3	Tear resistance	111

5.3.1	Tear propagation	113
5.3.2	Tear strength	115
5.4	Compression set	117
<b>CHAPTER 6</b>	<b>ACOUSTIC BEHAVIOR</b>	<b>120</b>
6.1	Sound absorption coefficient of foam composites	120
6.2	Noise reduction coefficient of foam composites	124
6.3	Effect of coir fibres and tyre particles to sound absorption	126
6.4	Effect of morphology to the sound absorption	128
6.4.1	Effect of morphology on top and bottom layers to sound absorption	129
6.5	Effect of foam thickness to sound absorption	129
6.6	Summary of the acoustic results and discussion	130
<b>CHAPTER 7</b>	<b>VIBRATION TRANSMISSIBILITY</b>	<b>131</b>
7.1	Description of foam-block system in vibration transmissibility	131
7.1.1	Analytical of foam-block System	132
7.1.2	Compressive strain and stiffness of foam in foam-block system	134

7.1.3	Natural frequency of foam-block system (linearized model)	136
7.1.4	Frictional losses occurred in foam-block system	136
7.2	Results of vibration transmissibility test on foams developed	138
7.2.1	Damping property of foam composites developed	144
7.3	Results of vibration transmissibility test on conventional seat cushions	146
7.3.1	Comparison on the damping property of foam composites with seat cushions	149
7.4	Summary of the vibration results and discussion	151
<b>CHAPTER 8</b>	<b>CONCLUSION AND RECOMMENDATION</b>	<b>152</b>
8.1	Conclusion	152
8.2	Future recommendation	154
	<b>REFERENCES</b>	<b>155</b>
	<b>APPENDICES</b>	<b>163</b>
	<b>LIST OF ACHIEVEMENTS</b>	<b>225</b>
	<b>VITA</b>	

## LIST OF FIGURES

1.1	Major applications of flexible PU foam	1
1.2	Image of (a) coconut coir fibres and (b) waste rubbers from tyre	3
2.1	Polyurethane Pre-polymers	10
2.2	Applications of flexible PU foams	11
2.3	Gelation reaction or PU cross-linking reaction	12
2.4	Blow reaction between isocyanate and water	12
2.5	Development of flexible PU foam	14
2.6	Morphology of flexible PU foam	14
2.7	Sound absorption ratio of foam composites with fillers increase from 2.2, 4.3, and 6.3 weight ratio	20
2.8	CFD 40 for flexible PU foam containing commercial $\text{CaCO}_3$	21
2.9	(a) Foam block and (b) Layer cuts from foam	22
2.10	Acoustic performance of CNT-flexible PU foams	24
2.11	Coconut palm	27
2.12	Cross-section of tyre	30
2.13	SEM of the surface of alkali treated coir fibre	33
2.14	Damping ratio of each percentage of coir fibres at different modes	34
2.15	The microcellular structure of (a) PP/WGRT blend, and (b) Pure PP	36
2.16	Typical use of flexible PU foam in automotive seating	37



2.17	Global usage of alternative foam molding chemistries	38
2.18	Factors contributing to the comfort in vehicle	39
2.19	Vibration curve for normal (Polyol A) and high resilience foam	40
2.20	Data of peak transmissibility and resonance frequency varied with resin technologies, density and hardness	41
2.21	Typical occupied vertical vibration transmissibility output	42
2.22	A typical stress-strain curve resulting from a uniaxial compression test on sample of polyurethane foam	44
2.23	Force-deflection curve for foam material, with a dynamic hysteresis loop for small amplitude excitation	45
2.24	Typical high and low amplitude force-deflection curves for foam under dynamic state	46
2.25	Energy diagram of foam at different densities	47
2.26	Viscoelastic model	50
2.27	Model of packaging product	51
2.28	Motion transmissibility system	53
2.29	The designed of fixture of foam-block system based on studies of (a) White <i>et al.</i> (2000) and (b) Joshi (2010)	55
2.30	Schematic of setup for dynamic foam testing	56
2.31	Amplitude response of foam-block system at 30% mean compression	57
2.32	The results of nonlinear and viscoelastic properties identification	58
2.33	Frequency response of SDOF system for mass 2.5kg and different base acceleration level	59
3.1	Closed mould designed to fabricate foams; (a)	

	Assembly parts of mould, and (b) the actual mould fabricated	62
3.2	The apparatus used for coconut coir fibres preparation; (a) Granulator machine, (b) pH meter, and (c) variable rotor milled machine	63
3.3	Fillers prepared for composites fabrication; (a) Coir fibres, and (b) tyre particles	63
3.4	Alkaline treatment process	64
3.5	Total weight required for pure foam and foam composites developed	66
3.6	Schematic diagram of foams production route	67
3.7	Foams produced according to the formula listed in Table 3.1; (a) pure foam, (b) sample A, (c) sample B, (d) sample C, (e) sample D and, (f) sample E	67
3.8	The Set-up of vibration transmissibility test	68
3.9	Foam-block system developed	69
3.10	Mass-spring-dashpot system	72
3.11	The displacement and acceleration responses (as a function of time) of mass-spring-dashpot system	73
3.12	Foam model loaded with mass	74
3.13	Set-up of acoustic absorption test	76
3.14	XRF machine for elemental analysis	78
3.15	The (a) SEM machine and (b) Auto Fined Coater used for morphology study	78
3.16	The (a) TGA machine and (b) tools for put the fillers in crucible	79
3.17	Vertical band saw machine	80
3.18	Core foams; (a) pure foam, (b) sample A, (c) sample B, (d) sample C, (e) sample D, and (f) sample E	81
3.19	The UTM used to conduct the foams	

	compression test	82
3.20	Configuration of specimen used to conduct tear resistance test	83
3.21	Specimen inserted to the UTM machine	83
3.22	The thickness of foam measured using digital indicator from <i>Mitutoyo</i>	84
3.23	The fixture designed for conducting the compression set; (a) 10 specimens can be put on the bottom plate in a single testing and (b) the specimens were compressed to 50% of its original thickness by top plate which locked by screw nuts	85
4.1	Surface characteristics of (a) untreated and (b) treated coir fibres	87
4.2	The appearance of recycled tyre particles	88
4.3	The (a) TG and (b) derived TG (DTG) curves obtained from 16mg of untreated and treated coir	90
4.4	The (a) TG and (b) DTG curves obtained from 16.70mg of recycled tyre particles	93
4.5	The fabricated foam composite; (a) front view and (b) top view	95
4.6	Samples of flexible PU foams reinforced with 2.5wt% of fillers; (a) pure PU foam, (b) PU+2.5wt% F, (c) PU+2.5wt% P, (d) PU+2.5wt% (50F50P), (e) PU+2.5wt% (80F20P), and (f) PU+2.5wt% (80P20F)	96
4.7	Schematic drawing of surfaces in core of foam composite	98
4.8	SEM micrographs of foam composites which were captured from the surface perpendicular to the foaming direction	99
4.9	SEM micrographs of foam composites which	

	were captured from the surface parallel to the foaming direction	99
4.10	Mean cell size of foam composites	100
4.11	(a)-(c) SEM observation of bonding between coir fibres and recycled tyres with PU foams	102
5.1	Core Foams prepared for density and compression force deflection tests; (a) PU foam, (b) PU+2.5wt%F, (c) PU+2.5wt%P, (d) PU+2.5wt%(50F50P), (e) PU+2.5wt%(80F20P), and (f) PU+2.5wt%(80P20F)	104
5.2	Core density of foam composites and pure PU foam developed	104
5.3	SEM image of (a) treated coir fibre and (b) tyre particles bonded with PU	105
5.4	Compression force deflection (70%) carried out by UTM machine	106
5.5	Force deflection curves of foams up to 70% stroke strain	107
5.6	Compressive stress-strain curves of foams	107
5.7	The results of compressive modulus and compressive strength of foam composites developed	108
5.8	Energy absorption of foam composite as compared to pure foam	110
5.9	Force against stroke strain of foams during tear resistance test	112
5.9	The torn surface of (a) pure PU and (b) PU+2.5wt%(50F50P)	114
5.10	The foams were ruptured during the tear resistance test, (a) pure PU foam, (b) PU+2.5wt%P, and (c) PU+2.5wt%(50F50P)	115
5.11	Tear strength of foam composites as compared to pure foam	115

5.12	Compression set of foam composites	117
6.1	The images of foams (20mm and 40mm) used in sound absorption test	120
6.2	(a) Averaged sound absorption coefficient of 20mm top layers	121
	(b) Averaged sound absorption coefficient of bottom layer of foams	122
6.3	Averaged sound absorption coefficient of 40mm foam composites	123
6.4	NRC of top and bottom layer of 20mm foam composites	125
6.5	NRC of foam composites with 40mm thickness	126
7.1	Schematic diagram of foam-block system in vibration transmissibility test	132
7.2	The foam-block system was modeled as a mass-spring-damper system	132
7.3	The static stiffness of foams when loaded with a total mass of 944.48g	135
7.4	Natural frequencies of the “foam-block system” as a function of foam composites inserted to the system, as calculated from the linearized local working point that is with 2 blocks loaded to “foam-block system”	136
7.5	Displacement response of foam-block system in free-vibration test	137
7.6	Displacement transmissibility from base to moveable top plate, at (a) 1mm base excitation and (b) 1.5mm base excitation	139
7.7	Acceleration transmissibility from base to moveable top plate, at (a) 0.1g base excitation and (b) 0.15g base excitation	140
7.8	Averaged density of samples used in displacement transmissibility test	148

7.9	Comparison of damping ratios of foam composites with seat cushions
-----	---

150



## LIST OF TABLES

1.1	Description of thesis organization	7
2.1	Time consumed at each stage for flexible PU foam composites production	16
2.2	The compression results of PET filled foam and standard foam in various layers	22
2.3	Sound absorption properties of fumed silica- flexible PU foams	26
2.4	Chemical composition of coir fibre	28
2.5	Mechanical properties of coir and synthetic fibres	28
2.6	Composition by weight of car and truck tyres	30
2.7	Tensile strength of the coir/polypropylene composites	35
3.1	Formulation of flexible PU foam composites	65
3.2	System control parameters	71
4.1	XRF analysis of untreated and treated coir fibres	88
4.2	XRF analysis of recycled tyre particles	89
4.3	Thermogravimetric (TG) results for coconut coir fibres	91
4.4	Thermogravimetric (TG) results for recycled tyre particles	93
5.1	Tear propagation occurred in foams during testing	113
5.2	Average value of compression set of foam composites	118
6.1	(a) Average value of sound absorption	

	coefficient versus frequency of 20mm top layers	122
	(b) Average value of sound absorption coefficient versus frequency of 20mm bottom layers	123
6.2	Average value of sound absorption coefficient versus frequency of 40mm foam composites	124
7.1	Averaged compressive strain of foams	134
7.2	The averaged damping ratio obtained by free-vibration test	138
7.3	(a) Data of resonance peak varied with fabricated foams and base excitation	141
	(b) Data of resonance frequency varied with fabricated foams and base excitation	142
	(c) Data of attenuation frequency varied with fabricated foams and base excitation	143
	(d) Data of transmissibility at 6Hz varied with fabricated foams and base excitation	143
7.4	(a) Damping ratio of foams obtained by data measured from displacement transmissibility test	145
	(b) Damping ratio of foams obtained by data measured from acceleration transmissibility test	145
7.5	(a) Averaged vibration characteristics of seat cushions, at 1mm base excitation	147
	(b) Averaged vibration characteristics of seat cushions, at 1.5mm base excitation	147
7.6	Damping ratio of seat cushions obtained by data measured from displacement transmissibility test	150



## LIST OF SYMBOLS

$E'$	- Storage modulus
$E''$	- Loss modulus
$\tan \delta$	- damping factor
$\sigma$	- stress
$\epsilon$	- strain
$\rho, D$	- Density
$F_k$	- Elastic force
$k, K_1, K_2, K_c$	- stiffness
$k_3, k_5$	- Nonlinear stiffness
$x, z$	- Displacement in uniaxial compression
$\Gamma(t-\tau)$	- Material's relaxation kernel or viscoelastic strain-impulse response
$t$	- Time
$\tau$	- Time variable
$E$	- Instantaneous modulus
$D^\beta \sigma(t)$	- Fractional derivative operator of the stress $\sigma(t)$
$\beta, E_s, E_0, E$	- Viscoelastic parameters (equation 2.3)
$c\dot{z}$	- Linear viscous damping in uniaxial compression
$c, C_1, C_2, C_c$	- Damping coefficient or damping constant
$\xi$	- Damping ratio
$X_0, Y_0, Z_0$	- Dimension of cubic cushion model
$A$	- Contact area
$D$	- Original cushion thickness
$W, M, m$	- Total mass or total riding mass
$\omega_n$	- Natural frequency
$\omega$	- Forced frequency

$\omega_b$	- Base frequency
$x, X$	- Passenger or mass motion (output)
$y, Y$	- Base motion (Input)
$\theta_1, \theta_2$	- Phase angle
$m\ddot{x}$	- Inertia force
$c(\dot{x} - \dot{y})$	- Damping force caused by motion input to output
$k(x - y)$	- Restoring or elastic force
$r$	- Frequency ratio
$K_x, K_y, K_z$	- Stiffness in x, y, or z axis
$S$	- Structural coefficient
$J$	- Energy
$V$	- Volume
$T$	- Thickness of foam when in tear resistance test
$C_t$	- Compression set (measured in thickness) in percentage
$t_o, t_f$	- Original thickness and final thickness
$\alpha$	- Sound absorption coefficient or viscoelastic parameter
$T_r$	- Transmissibility
$B$	- Damping parameter (equation 7.3)
NCO	- Reactive isocyanate group (-N=C=O)
$R$	- Reactive group from isocyanate
$R'$	- Reactive group from polyol
pH	- Activity of the (solvated) hydrogen ion
$C_nH_{2n}$	- Hydrocarbon chemical group
$C_nH_{2n-1}$	- Hydrocarbyls chemical group
$(CH_2O)_n$	- Group of natural saccharine
$n$	- 1, 2, 3 ...
$Y_1, Y_2, Y_3, Y_4$	- Displacement amplitude (Figure 7.5 or equation 7.3)
$\beta$	- logarithmic decrement (equation 7.3)
$i$	- 1, 2, 3 ...

**LIST OF APPENDICES**

A	Categories of post-consumer tyre materials	163
B	Foam models	164
C	Integration process of cushion material	167
D	Free-vibration decrement method	169
E	Methodology chart of the research	170
F	Mechanical properties	171
G	Sound absorption properties	189
H	Vibration transmissibility data	204



PTTA UTHM  
PERPUSTAKAAN TUNKU TUN AMINAH

## LIST OF ABBREVIATIONS

PU	- Polyurethane
F	- Treated Coir Fibres
P	- Recycled Tyre Particles
PET	- Polyethylene Terephthalate
US	- United States
wt.	- weight
SEM	- Scanning Electron Microscopy
XRF	- X-Ray Fluorescence
TGA	- Thermogravimetric Analysis
ASTM	- American Society for Testing and Materials
TDI	- Toluene Diisocyanate
MDI	- Methylene Diphenyl Diisocyanate
UV	- Ultraviolet
CFD	- Compression Force Deflection
Php	- Part By Hundred Parts Of Polyol
T	- Top
B	- Bottom
MT	- Mid-Top
MB	- Mid-Bottom
CNT	- Carbon Nanotubes
SBR	- Styrene-Butadiene Rubber
BR	- Butadiene Rubber
IIR	- Butyl Rubber
DMA	- Dynamic Mechanical Analysis
DMTA	- Dynamic Mechanical Thermal Analysis
NR	- Natural Rubber
WGRT	- Waste Ground Rubber Tire

## REFERENCES

- Alonso, M. V., Auad, M. L., & Nutt, S. (2006). Short Fiber-Reinforced Epoxy Foams. *Composite: Part A*, 37(11), 1952-1960.
- ASTM International (2008). *Flexible Cellular Materials-Slab, Bonded, and Molded Urethane Foams*. West Conshohocken, United States of America: D3574-08
- ASTM International (2010). *Impedance and Absorption of Acoustical Materials Using A Tube, Two Microphones and A Digital Frequency Analysis System*. West Conshohocken, United states of America: E1050-10
- Balachandran, B., & Magrab, E. B. (2004). *Vibrations*. California: Thomson.
- Bledzki, A. K., Zhang, W. Y., & Andris, C. (2001). Natural-Fibre-Reinforced Polyurethane Microfoams. *Composites Science And Technology*, 61(6), 2405-2411.
- Borlea, A., Rusu, T., Ionescu, S., Cretu, M., & Ionescu, A. (2011). Acoustical Materials-Sound Absorbing Materials Made of Pine Sawdust. *Romanian Journal of Acoustic and Vibration*, VIII(2), 95-98.
- Broos, R., Sonney, J. M., Thanh, H. P., & Casati, F. M. (2000). Polyurethane Foam Molding Technologies for Improving Total Passenger Compartment Comfort. *Proceedings of the Polyurethane Conference 2000*. Boston: CRC press. pp. 341-353.
- Bujang, I. Z., Awang, M. K., & Ismail, A. E. (2009). Influence of Fiber Volume Fraction on the Tensile Properties and Dynamic Characteristics of Coconut Fiber Reinforced Composite. *Journal of Science and Technology*, 1(1), 55-71.
- Chandra, A., Singh, S. P., & Gupta, K. (1999). Damping Studies in Fiber-Reinforced Composites-A Review. *Composite Structure*, 46(1), 41-51.
- Clausi, R. N., & Diloreto, S. (2009). *Highly Filled Composite Materials*. U.S. Patent 20090053490.

- Dai, X. H., Liu, Z. M., Wang, Y., Yang, G. Y., Xu, J., & Han, B. X. (2005). High Damping Property of Microcellular Polymer Prepared by Friendly Environmental Approach. *J. of Supercritical Fluids*, 33(3), 259-267.
- de Silva, C. W. (2007). *Vibration: Fundamental and Practice*. 2<sup>nd</sup>. ed. Boca Raton: CRC Press.
- Department of Defense Handbook (1997). *Package Cushion Design*. United States of America: MIL-HDBK-304C.
- Deng, R., Davies, P., & Bajaj, A. K. (2003). Flexible Polyurethane Foam Modelling and Identification of Viscoelastic Parameters for Automotive Seating Applications. *Journal of Sound and Vibration*, 262(3), 391-417.
- Food and Agriculture Organization. (2009). Natural Fibres-Coir. *International Year of Natural Fibres 2009*. Retrieved May 24, 2011, from <http://www.naturalfibres2009.org/en/fibres/coir.html>
- Fukumori, K., & Matsushita, M. (2003). Material Recycling Technology of Crosslinked Rubber Waste. *R&D Review of Toyota CRDL*, 38(1), 39-47.
- Gay, D. (2003). *Composite Materials: Design And Applications*. (Hoa, S. V. & Tsai, S. W. Trans.) Florida: CRC Press.
- Geethamma, V. G., Kalaprasad, G., Groeninckx, G., & Thomas, S. (2005). Dynamic Mechanical Behaviour of Short Coir Fiber Reinforced Natural Rubber Composites. *Composites: Part A*, 36(11), 1499-1506.
- Gibson, L. J., & Ashby, M. F. (1997). *Cellular Solids: Structure and Properties*. 2<sup>nd</sup>. ed. Cambridge: Cambridge University Press.
- Gibson, R. F. (2007). *Principles of Composite Material Mechanics*. 2<sup>nd</sup>. ed. Boca Raton: CRC Press.
- Goga, V. (2010). Measurement of the Energy Absorption Capability of Polyurethane Foam. *POSTERUS.sk*. Retrived June 6, 2010, from <http://www.posterus.sk/?p=4244&output=pdf>
- Gu, H. (2009). Tensile Behaviours of the Coir Fibre and Related Composites after NaOH Treatment. *Material and Design*, 30(9), 3931-3934.
- Holbery, J., & Houston, D. (2006). Natural-Fiber-Reinforced Polymer Composites in Automotive Applications. *Journal of Minerals, Metals and Material Society*, 58(11), 80-86.
- Indian Rubber Institute (2000). *Rubber Engineering*. New York: McGraw-Hill.
- Inman, D. J. (2001). *Engineering Vibration*. 2<sup>nd</sup>. ed. New Jersey: Prentice-Hall.

- International Carbon Black Association. (2006). *What is Carbon Black?*. Retrieved April 25, 2012, from [http://www.carbon-black.org/what\\_is.html](http://www.carbon-black.org/what_is.html)
- John, M. J., & Anandjiwala, R. D. (2008). Recent Developments in Chemical Modification and Characterization of Natural Fiber-Reinforced Composites. *Polymer Composites*, 29(2), 187-207.
- Jones, D. I. (2001). *Handbook of Viscoelastic Vibration Damping*. West Sussex: John Wiley & Sons.
- Joshi, G. A. (2010). *Entitled Planar Whole-body Vibratory Response of a Nonlinear Multi-body Model of a Seat-occupant System with Polyurethane Foam*. Purdue University: Master Thesis.
- Joshi, G., Bajaj, A. K., & Davies, P. (2010). Whole-body Vibratory Response Study Using Nonlinear Multi-body Model of Seat-occupant System with Viscoelastic Flexible Polyurethane Foam. *Industrial Health*, 48(5), 663-674.
- Kaushiva, B. D. (1999). *Structure-Property Relationships of Flexible Polyurethane Foams*. Virginia Polytechnic Institute and State University: Ph.D. Dissertation.
- Kim, J. H., Choi, K. C., & Yoon, J. M. (2006). The Foaming Characteristic and Physical Properties of Natural Rubber Foams: Effects of Carbon Black Content and Foaming Pressure. *Journal of Industrial Engineering Chemistry*, 12(5), 795-801.
- Klempner, D., & Sendjarevic, V. (2004). *Polymeric Foams and Foam Technology*. 2<sup>nd</sup>. ed. Munich: Hanser.
- Kolich, M., Essenmacher, S. D., & McEvory, J. T. (2005). Automotive Seating: The Effect of Foam Physical Properties on Occupied Vertical Vibration Transmissibility. *Journal of Sound and Vibration*, 28(1-2), 409-416.
- Koshute, M. A., Blaszkiewics, M., & Neal, B. L. (2001). Benchmarking of Polyurethane Technologies for Automotive Seat Cushions. *Polyurethane Expo 2001*. Columbus: CRC Press. pp. 247-254.
- Kumar, N., Khandelwal, R., Meena, P., Chaki, T., Mahla, D., & Dasgupta, S. (2011). Chemical Analysis on Different Oils use in Tyre Tread Cap Compound. *Internatinal Journal of Chemical, Environmental and Pharmaceutical Research*, 2(1), 12-19.

- Latinwo, G. K., Aribike, D. S., Susu, A. A., & Kareem, S. A. (2010a). Effect of Differnet Filler Treatment on the Morphology and Mechanical Properties of Flexible Polyurethane Foam Composites. *Nature and Science*, 8(6), 23-26.
- Latinwo, G. K., Aribike, D. S., Oyekunle, L. O., Susu, A. A., & Kareem, S. A. (2010b). Effects of Calcium Carbonate of Different Composition and Particles Size Distribution on the Mechanical Properties of Flexible Polyurethane Foam. *Nature and Science*, 8(9), 92-101.
- Lee, E. K., & Choi, S. Y. (2007). Preparation and Characterization of Natural Rubber Foams: Effects of Foaming Temperature and Carbon Black Content. *Korean Journal of Chemistry Engineering*, 24(6), 1070-1075.
- Li, X., Tabil, L. G., & Panigrahi, S. (2007). Chemical Treatments of Natural Fiber for Use in Natural Fiber-Reinforced Composites: A Review. *Jornal of Polymer Environment*, 15(1), 25-33.
- Liang, J. W. (2005). Identifying Coulomb and Viscous Damping from Free-Vibration Acceleration Decrements. *Journal of Sound and Vibration*, 282(3-5), 1208-1220.
- Liang, J. W., & Feeny, B. F. (1998). Identifying Coulomb and Viscous Friction from Free-Vibration Decrements. *Nonlinear Dynamics*, 16(4), 337-347.
- Lin, G., Zhang, X. J., Liu, L., Zhang, J. C., Chen, Q. M., & Zhang, L. Q. (2004). Study on Microstructure and Mechanical Propeties Relationship of Short Fibres/Rubber Foam Composites. *European Polymer Journal*, 40(8), 1733-1742.
- Mahajerin, E., & Burgess, G. (2010). Investigation of Package Vibration During the Repetative Shock Test. *Proceeding of the World Congress on Engineering 2010 Vol II*. London: Newswood and International Association of Engineers. pp. 1016-1018.
- Mahmoud, A.-E. A., & El-Nagar, K. E. (2011). Characterization of the Acoustic Behaviours of Laminated Polyester Fabric Using Different Adhesion System. *Australian Journal of Basic and Appled Sciences*, 5(4), 96-101.
- Mar Bernal, M., Molenberg, I., Estravis, S., Rodriguez-Perez, M. A., Huynen, I., Lopez-Manchado, M. A., & Verdejo, R. (2012). Comparing the Effect of Carbon-Based Nanofillers on the Physical Properties of Flexible Polyurethane Foams. *Journal of Material Science*, 47(15), 5673-5679.



- McClellan, T. R., & Viejo, M. (1995). *Microcellular Polyurethane Composite*. U.S. Patent 5385953.
- Mehta, C. R., & Tewari, V. K. (2010). Damping Characteristic of Seat Cushion Material for Tractor Ride Comfort. *Journal of Terramechanics*, 47(6), 401-406.
- Mello, D. d., Pezzin, S. H., & Amico, S. C. (2009). The Effect of Post-Consumer PET Particles on the Performance of Flexible Polyurethane Foams. *Polymer Testing*, 28(7), 702-708.
- Milivojevich, A., Blair, G. R., Pageau, J. G., & van Heumen, J. D. (1999). Automotive Seating Comfort; Defining Comfort Properties in Polyurethane Foam. *SAE International Congress & Exposition*. Detroit: SAE International. pp. 1-10.
- Monteiro, S. N., Terrones, L. A., & D'Almeida, J. R. (2008). Mechanical Performance of Coir Fiber/Polyester Composites. *Polymer Testing*, 27(5), 591-595.
- Mothe, C. G., & de Miranda, I. C. (2009). Characterization of Sugarcane and Coconut Fibers by Thermal Analysis and FTIR. *Journal of Thermal Analysis and Calorimetry*, 97(2), 661-665.
- Murakami, S., Saiki, K., Hayashi, M., Satou, T., & Fukami, T. (2001). A Newly Developed MDI-Based Polyurethane Flexible Foam for Automotive Seat Cushion Having Both Superior Static and Dynamic Properties. *Journal of Cellular Plastics*, 37(3), 249-261.
- Patten, W. N., Sha, S., & Mo, C. (1998). A Vibration Model of Open Polyurethane Foam Automotive Seat Cushion. *Journal of Sound and Vibration*, 217(1), 145-161.
- Polyurethane Foam Association. (1991). Flexible Polyurethane Foam: A Primer, *INTOUCH*, 1(1), Retrieved May 25, 2011, from [http://www.pfa.org/intouch/new\\_pdf/lr\\_IntouchV1.1.pdf](http://www.pfa.org/intouch/new_pdf/lr_IntouchV1.1.pdf)
- Polyurethane Foam Association. (1992). Polyurethane Foam in Furniture Design, *INTOUCH*, 2(3), Retrieved May 25, 2011, from [http://www.pfa.org/intouch/new\\_pdf/lr\\_IntouchV2.3.pdf](http://www.pfa.org/intouch/new_pdf/lr_IntouchV2.3.pdf)
- Polyurethane Foam Association. (1996). Flexible Polyurethane Foam in Packaging, *INTOUCH*, 5(2), Retrieved May 25, 2011, from [http://www.pfa.org/intouch/new\\_pdf/hr\\_IntouchV5.2.pdf](http://www.pfa.org/intouch/new_pdf/hr_IntouchV5.2.pdf)

- Polyurethane Foam Association. (1997). Flexible Polyurethane Foam in Transportation Industry. *INTOUCH*, 6(1), Retrived May 25, 2011, from [http://www.pfa.org/intouch/new\\_pdf/lr\\_IntouchV.6.1.pdf](http://www.pfa.org/intouch/new_pdf/lr_IntouchV.6.1.pdf)
- Rajkumar, K., Ranjith, P., & Thavamani, P. (n.d.). *Modified Coconut pith-a novel Rubber Additive for Rubber Industry*. Retrieved May 7, 2011, from Indian Rubber Manufacturing Research Association: [http://www.irmra.org/naip/pdfs/paper\\_publication.pdf](http://www.irmra.org/naip/pdfs/paper_publication.pdf)
- Rao, S. S. (2005). *Mechanical Vibrations*. 4<sup>th</sup>. ed. Singapore: Prentice Hall.
- Rosa, M. F., Chiou, B.-s., Medeiros, E. S., Wood, D. F., Williams, T. G., Mattoso, L. H., Orts, W. J., & Imam, S. H. (2009). Effect of Fiber Treatment on Tensile and Thermal Properties of Starch/Ethylene Vinyl Alcohol Copolymers/Coir Biocomposites. *Bioresource Technology*, 100(21), 5196-5202.
- Sankar, H. R., Krishna, P. V., Rao, V. B., & Babu, P. B. (2010). The Effect of Natural Rubber Particle Inclusions on the Mechanical and Damping Properties of Epoxy-Filled Glass Fibre Composites. *Proceeding of the Institution of Mechanical Engineers, Part L: Journal of Material Design and Applications*. 224(2), 63-70.
- Sant'Anna, S. S., de Souza, D. A., de Araujo, D. M., de Freitas Carvalho, C., & Yoshida, M. I. (2008). Physico-Chemical Analysis of Flexible Polyurethane Foams Containing Commercial Calcium Carbonate. *Material Research*, 11(4), 433-438.
- Sasaki, T., Wada, H., Horie, A., Harada, H., Murata, Y., & Takagi, D. (2003). *Novel Polyether Polyol Designed for High Performance Automotive Seating Foams*. Report Research Lab Asahi Glass Urethane Co.Ltd.
- Scuracchio, C. H., Waki, D. A., & da Silva, M. (2007). Thermal Analysis of Ground Tire Rubber Devulcanized by Microwaves. *Journal of Thermal Analysis and Calorimetry*, 87(3), 893-897.
- Seddeq, H. S. (2009). Factors Influencing Acoustic Performance of Sound Absorption Materials. *Australian Journal of Basic and Applied Sciences*, 3(4), 4610-4617.
- Shulman, V. L. (2004). *Tyre Recycling*. vol. 15. Shropshire: Rapra Technology.
- Singh, R., Davies, P., & Bajaj, A. K. (2003). Estimation of the Dynamical Properties of Polyurethane Foam through use of Prony Series. *Journal of Sound and Vibration*, 264(5), 1005-1043.

- Siswanto, W. A., Ibrahim, M. N., Madlan, M. A., & Mohamad, S. M. (2011). Shaker Table Design for Electronic Device Vibration Test System. *International Journal of Engineering and Technology*, 3(6), 663-667.
- Strong, A. B., & Rotz, C. A. (1999). Damping In Composites - It's There, But Is It Understood?. *Composites Fabrication*, pp. 30-37. Retrieved May 7, 2011, from <http://strong.groups.et.byu.net/pages/articles/articles/damping.pdf>
- Suddell, B. C. (2009). Industrial Fibers: Recent and Current Developments. *Proceedings of the symposium on Natural Fibres*, (pp. 71-82).
- Sukontasukkul, P. (2009). Use of Crumb Rubber to Improve Thermal and Sound Properties of Pre-Cast Concrete Panel. *Construction and Building Materials*, 23(2), 1084-1092.
- Sung, C. H., Lee, K. S., Lee, K. S., Oh, S. M., Kim, J. H., Kim, M. S., & Jeong, H. M. (2007). Sound Damping of a Polyurethane Foam Nanocomposite. *Macromolecular Research*, 15(15), 443-448.
- Taj, S., Munawar, M. A., & Khan, S. (2007). Natural Fiber-Reinforced Polymer Composite. *Proceeding of the Pakistan Academic of Science*, 44(2), 129-144.
- Tewari, V. K., & Prasad, N. (1999). Three-DOF Modelling of Tractor Seat-Operator System. *Journal of Terramechanics*, 36(4), 207-219.
- Ting, L., LiangLiang, M., Fuwei, L., Wuzhou, J., Zhaobo, H., & Pengfei, F. (2011). Preparation, Structure, and Properties of Flexible Polyurethane Foams Filled with Fumed Silica. *Journal of Natural Sciences*, 16(1), 029-032.
- Verdejo, R., Stampfli, R., Alvarez-Lainez, M., Mourad, S., Rodriguez-Perez, M. A., Bruhwiler, P. A., & Shaffer, M. (2009). Enhanced Acoustic Damping in Flexible Polyurethane Foams Filled with Carbon Nanotubes. *Composites Science and Technology*, 69(10), 1564-1569.
- Wang, Y., & Low, K. H. (2005). Damped Response Analysis of Nonlinear Cushion Systems by a Linearization Method. *Computers and Structures*, 83(19-20), 1584-1594.
- White, S. W., Kim, S. K., Bajaj, A. K., & Davies, P. (2000). Experimental Techniques and Identification of Nonlinear and Viscoelastic Properties of Flexible Polyurethane Foam. *Nonlinear Dynamics*, 22(3), 281-313.
- Widdle, R. D. (2005). *Measurement and Modelling of the Mechanical Properties of Flexible Polyurethane Foam*. Purdue University: Ph.D. Dissertation.

- Wu, D. Y., Bateman, S., & Partlett, M. (2007). Ground Rubber/Acrylonitrile-Butadiene-Styrene Composites. *Composites sciences and Technology*, 67(9), 1909-1919.
- Xin, Z. X., Zhang, X. Z., Pal, K., Byeon, J. U., Lee, S. H., & Kim, J. K. (2010). Study of Microcellular Injection-Molded Polypropylene/Waste Ground Rubber Tire Powder Blend. *Materials and Design*, 31(1), 589-593.
- Zhang, L. (2008). *Structure-Property Relationship of Polyurethane Flexible Foam Made From Natural Oil Polyols*. University of Minneapolis: Ph.D. Dissertation.
- Zhang, L. F., Yilmaz, E. D., Schjodt-Thomsen, J., Rauhe, J. C., & Pyrz, R. (2011). MWNT reinforced Polyurethane Foam: Processing, Characterization and Modelling of Mechanical Properties. *Composite Science and Technology*, 71(6), 877-884.
- Zhang, L., & Dupuis, R. (2010). Measurement and Identification of Dynamic Properties of Flexible Polyurethane Foam. *Jornal of Vibration and Control*, 17(4), 517-526.



PTTA UTHM  
PERPUSTAKAAN TUNKU AMINAH